

APPLICATION

t should be installed outdoors on a compacted aggregate base.

This is a high use field product. This product should be installed outdoors on a compacted aggregate base. The PowerHouse series is made up of some of the most proven and durable fibers in the world. The 2C "Double Coverage" system allows for more face yarn to show off its beautiful colors. This 13,000 denier system will keep your field looking newer, longer.

ArmorLoc ** 3L



MEMBER ASSOC

MERICAN PORTS BUILDERS SOCIATION CERTIFIED FIELD BUILDER-Synthe



*Custom colors available upon request

200 Howell Dr. Dalton GA 30721 www


www.sporturf.com 800

```
800.798.1056
```

TESTING

POWERHOUSE 40 Z

FINISHED FABRIC	ENGLISH SYSTEM		METRIC	SYSTEM	ASTM TEST
Nominal Specification	Value	Units	Value	Units	Method
Pile Height (Nominal)	2	In.	50.80	mm.	D-5823
Face Weight	40	oz/yd²	1356	g/m²	D-5848
Total Fabric Weight	67	oz/yd²	2272	g/m²	D-5848
Primary backing Weight	7.4	oz/yd²	251	g/m²	D-5848
Secondary Coating Weight	22	oz/yd²	746	g/m²	D-5848
Tuft Bind	>10	lbs.	>4.5	Kg.	D-1335
Grab Tear Strength (Average)	>200	lbs.	>91	Kg.	D-2256
Lead Content	<50	ppm	<50	ppm	D-2765
Total Yarn Linear Density	13,000	Denier	14,445	D-Tex	D-1577
Tensile Strength (Slit)	8	lbs.	3.6	Kg.	D-789
Stitch Rate	8	Per 3"	10.5	Per 10 cm	D-5793
Machine Gauge	1/2	In.	1.27	Cm.	D-5793
Flammability	TEST	PASSED	TEST	PASSED	D-2859
Water Permeability w/infill	>30	In./Hr.	>76	Cm./Hr.	F-1551
Fiber Thickness (Slit)	9.4	mils	100	microns	D-3218
Fabric Width	15	Ft.	4.6	М	None



It is the policy of Sporturf[™] to continuously improve their line of products. Therefore, Sporturf[™] reserves the right to change, modify or discontinue systems, specifications and accessories of all products at any time without notice or obligation to purchaser.