

PL705

800.798.1056

TESTING

SPORTURF 36 PL705

FINISHED FABRIC

ENGLISH SYSTEM

METRIC SYSTEM

ASTM TEST

<i>Nominal Specification</i>	<i>Value</i>	<i>Units</i>	<i>Value</i>	<i>Units</i>	<i>Method</i>
Pile Height (Nominal)	.5625	In.	14.288	mm.	D-5823
Face Weight	36	oz/yd ²	1,221	g/m ²	D-5848
Total Fabric Weight (SilverBack™)	63	oz/yd ²	2,136	g/m ²	D-5848
Total Fabric Weight (Greenback)	84	oz/yd ²	2,848	g/m ²	D-5848
Total Fabric Weight (5mm Foam)	118	oz/yd ²	3345.24	g/m ²	D-5848
Primary Backing Weight	7	oz/yd ²	237	g/m ²	D-5848
Secondary Coating Weight (SilverBack™)	20	oz/yd ²	678	g/m ²	D-5848
Secondary Coating Weight (Greenback)	41	oz/yd ²	1,390	g/m ²	D-5848
Secondary Coating Weight (5mm Foam)	78	oz/yd ²	2,645	g/m ²	D-5848
Grab Tear Strength (Average)	>200	lbs.	>91	kg.	D-2256
Lead Content	<50	ppm	<50	ppm	D-2765
Total Yarn Linear Density	4,600	Denier	5,111	D-Tex	D-1577
Stitch Rate	19	Per 3"	24.89	Per 10 cm	D-5793
Machine Gauge	3/16"	In.	.48	cm	D-5793
Flammability	TEST	PASSED	TEST	PASSED	D-2859
Fabric Width	12	Ft.	4.6	M	None

8/28/2023